



TECHNICAL DATA SHEET

DAP® Concrete Bonding Additive

PRODUCT DESCRIPTION

DAP® Concrete Bonding Additive is an advanced vinyl compound that can be used to create a high moisture resistant, high density concrete. As a primer, DAP Concrete Bonding Additive is perfect for new or old concrete patching, resurfacing and leveling. It is excellent for capping walls, patching steps and tuck pointing. For interior and exterior use.



PACKAGING	COLOR	UPC
Quart	White	7079802131
Gallon	White	7079802132

KEY FEATURES & BENEFITS

- Bonds old concrete to new concrete
- For capping walls, resurfacing, patching & tuck pointing
- Primer and Admix in one
- Multi-Use adhesion
- Interior/Exterior

SUGGESTED USES

Ideal for applying as a coating or mixing into mortar for:

- Repairing cracks in steps, walks, driveways and patios.
- Tuck pointing old mortar joints of brick and concrete.
- Resurfacing and leveling of old concrete slabs and walls



TECHNICAL DATA SHEET

PERFORMANCE CHARACTERISTICS

- Locks in moisture to allow for improved curing of concrete.
- Stops moisture suction into old concrete to ensure perfect patching.
- Enables resurfacing with a thin layer of concrete without cracking.
- May be applied as a coating or mixed into mortar for repairs

APPLICATION

Admix Solution:

- Prepare by making a solution of 1 measure of additive added to 4 measures of clean water.

Mortar Mix:

- Use packaged dry "Topping Mix" or 1 measure of Portland Cement mixed with 4 measures of sharp, clean sand.
- Add enough Admix Solution to the dry mix to form a stiff mortar. Thin, wet mixes cause shrinkage and cracking.

Patching Concrete Steps, Curbs or Joining New Concrete:

- Surface must be free of grease, oil and other foreign matter. Sweep or blow surface with compressed air to remove all mud, dirt, dust and other loose debris.
- Prime coat the surface to be patched with undiluted DAP® Concrete Bonding Additive. When the prime coat is tacky, apply fresh mortar which has been made using the Admix Solution. Do not allow the prime coat to dry out. If the prime coat does dry out, apply a second coating of the DAP Concrete Bonding Additive and repair immediately.

Tuck Pointing:

- For an extra strong mortar for brick, applying wall caps, tuck pointing and filling cracks, use a Mortar Mix as indicated above.

Resurfacing Walls and Floors:

- Remove all foreign material from concrete area to be resurfaced.
- TEST FOR BOND: Traces of silicates, silicones, etc., used for sealing and waterproofing, may prevent a bond of new material. Make a test patch before proceeding.
- PRIME with a mixture of 4 parts DAP Concrete Bonding Additive mixed with 1-part clean water. Use an extra prime coat on all areas where new concrete will be feather edged.
- WET THE CEMENT/SAND MIX with a solution of 1-part DAP Concrete Bonding Additive mixed with 4 parts clean water.

Caution: Use only sharp, crushed stone free of clay and humus along with an ample ratio of cement. Do not use river sand. DO NOT USE BELOW 50°F.



TECHNICAL DATA SHEET

TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Base:	Vinyl Acetate Copolymer
Volatile:	Water
Flash Point:	Nonflammable
Solids:	36.5
Weight/Gallon:	8.7 lbs.
Specific Gravity:	1.04
Odor:	Pleasant
Color:	White, dries translucent
Consistency:	Milky liquid
Temperature Application Range:	Above 50°F
Dry Time:	Approximately 45 min. when applied as a primer, depending on temp. & humidity. When used as an admix, allow for set times according to the cement mix supplier, typically 28 days for full cure.
Freeze/Thaw Stability:	Passes 5 Cycles
Coverage:	Approx. 350 sq. ft./gallon
Shelf Life:	12 month minimum
Coverage	Quart: Will prime and patch area plus reinforce a 60 lb. sack of dry-mix concrete. Gallon: Allow 1-gallon DAP® Concrete Bonding Additive per sack of pure dry cement or 1 to 1-1/2-gallon

CLEAN UP & STORAGE

Before drying, remove excess additive with a damp cloth. Dried additive must be cut of scraped away. Be sure container lid is closed and tightly sealed. Store at room temperature 40-80°F.