

Appearance: Grey, extruded butyl sealant tape.

Temperatures: Application: 30°F – 110° F Operating limits: -20°F – 275° F.

Low Temperature Flexibility: No cracking, no adhesion loss at -20°F.

Tensile Strength: 25psi (ASTM D987-72) with 200 % elongation (HTM 15.0).

Needle Penetration: 80 – 105 (ASTM D 217) (100GM WT @ 77° F).

Release Liner: Clearly released with no transfer of product compound (ASTM C879).

Water Resistance: Sealant maintains adhesion to galvanized metal after being submerged for 30 days at 120° F (HTM 9.0).

Chemical Resistance: Excellent to water, vapor and alcohol. Weaken to acids and bases. Avoid use with organic solvents.

Corrosivity: No staining, etching or other signs of corrosion on galvanized or coated metals (ASTM D3310).

Flammability: Nonflammable.

Shelf Life: 18 months – 2 years

Storage Temperature: 30° F – 110° F

Pressure Class: SMACNA 1/2, 1, 2, 3, 4, 6 and 10 in w.g.

Specifications: Military MIL-C-18969B, Type II, Class B. Federal TT-C789A, Type II, Class B.