

TPO	
Product Data	
Appearance	Non-gloss backing with gray adhesive sealant
Bonding Time	Immediate, water tight aggressive grip. Full Bond in 24 hours
Backing	6.5 mil UV Resistant TPO rubber
Adhesive	22 mil gray elastomeric modified butyl rubber
Temperatures	
Application	32°F (0°C) to 110°F (43°C)
Operating Limits	-40°F (-40°C) to 220°F (104°C)
Tensile Strength	4821 psi (at break) ASTM D 822
Elongation	900% (at break) ASTM D 822
Peel Strength	17 lbs. per linear inch
Water Resistance	Excellent
U.V. Resistance	Excellent

Aluminum	
Product Data	
Appearance	Mill finish aluminum substrate with gray adhesive sealant
Bonding Time	Instant high tack. Full Bond in 24 hours
Backing	Aluminum
Adhesive	22 mil gray elastomeric modified butyl rubber

Temperatures	
Application	35°F (2°C) to 110°F (43°C)
Operating Limits	-40°F (-40°C) to 220°F (104°C)
Tensile Strength	720 psi average
Elongation	560% Average
Peel Strength	>10 lbs. per linear inch
Water Resistance	Passes 2000 hours QUV (ASTM G53)

NOW AVAILABLE IN TAN!

Part Number	Type	Color	Size
522TPO-4125-1C	TPO	White	4" X 12.5' Roll
522TPO-425-1C	TPO	White	4" X 25' Roll
522TPO-450-1C	TPO	White	4" X 50' Roll
522TPO-66-1C	TPO	White	6" X 6" Patch
522TPOT-4125-1C	TPO	Tan	4" X 12.5' Roll
522TPOT-425-1C	TPO	Tan	4" X 25' Roll
522TPOT-450-1C	TPO	Tan	4" X 50' Roll
522AF-450-1C	Foil		4" X 50' Roll
522AF-66-1C	Foil		6" X 6" Patch

[Rely on premium RV roofing and sealants by Dicor if you're looking for quality and efficiency.](#)